

1 **(April 7, 2003)**

2 ***Pigmented Sealer***

3 The pigmented sealer shall be a semi-opaque colored toner containing only methyl
4 methacrylate-ethyl acrylate copolymer resins, toning pigments suspended in solution at
5 all times by a chemical suspension agent, and solvent. Toning pigments shall be
6 laminar silicates, titanium dioxide and inorganic oxides only. There shall be no settling
7 or color variation. Use of vegetable or marine oils, paraffin materials, stearates or
8 organic pigments in any part of coating formulation will not be permitted.

9
10 The color shall match the color chip Washington Gray. Pigmented sealer color chips
11 are available from the State Bridge and Structures Architect, WSDOT Bridge and
12 Structures Office, P. O. Box 47340, Olympia, WA 98504-7340.

13
14 The pigmented sealer shall be selected from the approved products listed in the
15 WSDOT Qualified Products List, latest edition.